


FP-530 OPACITY PIGMENT

FP-530 is unique opacity pigment powder for use in plastic applications. FP-530 is designed to give optimal optical properties enabling replacement of TiO₂ in plastics.

FP-530 TYPICAL PIGMENT PROPERTIES

These are typical values but do not constitute specifications.

Dry Solids	%	min. 99,0
Brightness (ISO)		95,0 ± 0,5
L* value		98,8 ± 0,3
a* value		-0,40 ± 0,10
b* value		1,65 ± 0,10
Specific Surface Area (BET)	m ² /g	10,0 ± 1,5
Average Particle Size	µm	1,0 ± 0,1
Specific Gravity	kg/dm ³	~ 2,8
Surface charge		cationic



DISCLAIMER OF LIABILITY The information herein is based on technical data that we believe is accurate and reliable. However, the information is provided without any warranty, express or implied, regarding its correctness. The conditions or methods of use this information are beyond our control. For this and other reasons, we do not assume responsibility and express disclaim liability for loss, damage or expense arising out of or in any way connected with any use of this information.

FP-Pigments GmbH
Am Haupttor 2176
DE-06237 Leuna
DEUTSCHLAND
www.fp-pigments.com

Telefon:
+49 (0) 3461 43 77 00
Telefax:
+49 (0) 3461 43 77 10

Bank:
Nordea Bank Finland Plc, Niederlassung Deutschland
Kto.-Nr. 644 153 0002, (BLZ 514 303 00)
IBAN: DE66514303006441530002
SWIFT: NDEADEF